



Docket No.: 0756-7243

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Patent Application of:)
Kazuo NISHI et al.)
Application No.: 10/749,552) Examiner: Unknown
Filed: January 2, 2004) Group Art Unit:
For: SEMICONDUCTOR DEVICE AND METHOD) Not Yet Assigned
OF MANUFACTURING THEREOF)

VERIFICATION OF TRANSLATION

Commissioner for Patents
P.O.Box 1450
Alexandria, VA 22313-1450

Sir:

I, Etsuko FUJIMOTO, C/O Semiconductor Energy Laboratory Co., Ltd. 398, Hase, Atsugi-shi, Kanagawa-ken 243-0036 Japan, herewith declare:

that I am well acquainted with both the Japanese and English Languages; and

that to the best of my knowledge and belief the followings is a true and correct translation of the US Patent Application No. 10/749,552 filed on January 2, 2004.

I further declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

Date: this 1 day of November, 2004

Etsuko Fujimoto

Name: Etsuko FUJIMOTO

DESCRIPTION

SEMICONDUCTOR DEVICE AND METHOD OF MANUFACTURING THEREOF

5 TECHNICAL FIELD

The present invention relates to a method of manufacturing a thin and lightweight semiconductor device. Specifically, the present invention relates to a method for manufacturing a semiconductor device over an organic resin member or a plastic substrate. In the present invention, a semiconductor device is a semiconductor device including a semiconductor element having an amorphous semiconductor film as an active region and a semiconductor element having a crystalline semiconductor film as an active region, specifically, a semiconductor device including an optical sensor element, a photoelectric conversion device, a solar battery, or the like.

BACKGROUND ART

20 An optical sensor is used as a sensor for converting an image into an electrical signal in a wide range of fields such as a facsimile machine, a copying machine, a video camera, and a digital still camera. Mainly, a semiconductor is used as a material of the optical sensor, and silicon can be given as a typical example of a semiconductor material. As the optical sensor using silicon, there are an optical sensor using a single crystal silicon or polysilicon film and an optical sensor using an amorphous silicon film. The optical sensor using the single crystal silicon or polysilicon film has a sensitivity peak in 25 an infrared region in the proximity of 800 nm, and has 30

sensitivity up to in the proximity of 1100 nm. Consequently, in the case of sensing a white fluorescent light which hardly includes a spectrum of an infrared region and sunlight which has a wide range of spectra from an ultraviolet region to an infrared region, there is a problem that detected results of each light are different even though actual illuminance is equal.

On the other hand, the optical sensor using amorphous silicon has little sensitivity to light in an infrared region, a sensitivity peak in the proximity of from 500 nm to 600 nm which is in the center of wavelength of a visible light region, and sensing characteristics similar to human spectral luminous efficacy. Therefore, the one using amorphous silicon is preferable as the optical sensor.

The optical sensor using amorphous silicon can be roughly divided into 1) a resistor type and 2) a diode type. The resistor type can provide a large current since it has an amplification effect as a transistor. However, an amplified optical charge does not disappear even after light is blocked since a large quantity of optical charges is generated by amplification. Therefore, response speed thereof is slow, and a dynamic range due to contrast of light is narrow.

Meanwhile, the diode type optical sensor has a depletion layer spreading in amorphous silicon, and easily detects an optical charge generated when light enters. It has high response speed since it does not have an amplification effect, and a dynamic range due to contrast of light is wide. However, a capacitor for retaining a charge or an element for amplifying and outputting an optical charge is required since current due to the optical charge is small.

As an element for amplifying and outputting a current detected by the optical sensor as an output signal by time division (hereinafter, referred to as an amplifying element), there are a bare IC type using a field effect transistor of a single crystal semiconductor (mainly, a silicon semiconductor) and a TFT type using a thin film transistor using a thin amorphous silicon film or polysilicon film as a channel formation region.

An IC type optical sensor has high speed and high reliability as the amplifying element. However, cost is very high since as many bare chip ICs as the optical sensors are required. In addition, both a substrate over which a photoelectric conversion element (photoelectric conversion layer) made of amorphous silicon or the like is to be formed and a bare IC chip are necessary. Therefore, occupied area in an installation substrate such as a printed wiring board is enlarged, which becomes an obstacle to downsizing of an electronic device equipped with the optical sensor.

Meanwhile, an active region of a TFT that is the amplifying element and a photoelectric conversion layer of the photoelectric conversion element can be formed over the same substrate in the TFT type optical sensor. Therefore, occupied area in an installation substrate such as a printed wiring board can be narrowed; consequently, downsizing of the electronic device equipped with the optical sensor is easy. Further, a cost thereof is low compared with that of the IC type optical sensor using single crystal silicon. Since a TFT using a polysilicon film has higher electrical characteristics than that of a TFT using an amorphous silicon film, high-speed response as the amplifying element is possible. Accordingly, it is effective for detecting even a weak photoelectric current

to form the amplifying element with the TFT using a polysilicon film (for example, Japanese Patent Laid-Open No. H6-275808 (pp. 3 to 4, FIG. 1)).

However, the optical sensor using a TFT having an active
5 region made of a polysilicon film as the amplifying element, as disclosed in Japanese Patent Laid-Open No. H6-275808, has limitation on the kind of a substrate due to its manufacturing process. Typically, only a substrate that can withstand
10 crystallization temperature or activation temperature of silicon, such as quartz or glass can be used. This is because a heating step at a comparatively high temperature (for example, equal to or more than 500 °C) is required for crystallization or activation of silicon. These substrates have thick film
15 thickness, which causes a problem of increase in parts volume and weight of the optical sensor.

Since glass or the like does not have flexibility, an installation site of the optical sensor is over a flat portion, specifically, over a printed wiring board, and there is limitation on the installation site. Therefore, an attempt to
20 use lightweight and thin, preferably, flexible plastic, or the like as a substrate of the optical sensor has been made. Plastic is lightweight and thin; however, it has a low allowable temperature limit. There is a problem that it is difficult to form the TFT having an active region made of a polysilicon film
25 over this substrate.

In view of the above problems, it is an object of the present invention to manufacture a semiconductor device including a semiconductor element having an active region made of a polysilicon film and a semiconductor element having an
30 active region made of an amorphous silicon film, typically, a

semiconductor device including an optical sensor, a photoelectric conversion element, or a solar battery element over a lightweight and thin, preferably, flexible substrate or organic member.

5

DISCLOSURE OF INVENTION

The present invention is a method for manufacturing a semiconductor device, characterized by comprising the steps of: forming a metal film, an insulating film, and a first amorphous semiconductor film in sequence over a first substrate; crystallizing the first amorphous semiconductor film; forming a first semiconductor element by using the crystallized semiconductor film as an active region; attaching a support to the first semiconductor element; causing separation between the metal film and the insulating film; forming a second amorphous semiconductor film over the first semiconductor element after attaching a second substrate to the separated insulating film and separating the support; and forming a second semiconductor element using the second amorphous semiconductor film as an active region.

It may be a method for manufacturing a semiconductor device, characterized by comprising the steps of: forming a metal film, an insulating film, and a first amorphous semiconductor film in sequence over a first substrate; crystallizing the first amorphous semiconductor film; forming a first semiconductor element by using the crystallized semiconductor film as an active region; forming a second amorphous semiconductor film; forming a second semiconductor element using the second amorphous semiconductor film as an active region; attaching a support to the first semiconductor

element and the second semiconductor element; and causing separation between the metal film and the insulating film.

It may be a method for manufacturing a semiconductor device, characterized by comprising the steps of: forming a
5 metal film, an insulating film, and a first amorphous semiconductor film in sequence over a first substrate; crystallizing the first amorphous semiconductor film; forming a first semiconductor element by using the crystallized semiconductor film as an active region; forming a second
10 amorphous semiconductor film; forming a second semiconductor element using the second amorphous semiconductor film as an active region; attaching a support to the first and the second semiconductor elements; causing separation between the metal film and the insulating film; and separating the support after
15 attaching a second substrate to the separated insulating film.

It may be a method for manufacturing a semiconductor device, characterized by comprising the steps of: forming a metal film, an insulating film, and a first amorphous semiconductor film in sequence over a first substrate;
20 crystallizing the first amorphous semiconductor film; forming a first semiconductor element by using the crystallized semiconductor film as an active region; attaching a support to the first semiconductor element by using an adhesive; causing separation between the metal film and the insulating film;
25 forming a second amorphous semiconductor film over the first semiconductor element after attaching a second substrate to the separated insulating film by using an adhesive bond; and forming a second semiconductor element using the second amorphous semiconductor film as an active region.

30 It may be a method for manufacturing a semiconductor

device, characterized by comprising the steps of: forming a metal film, an insulating film, and a first amorphous semiconductor film in sequence over a first substrate; crystallizing the first amorphous semiconductor film; forming
5 a first semiconductor element by using the crystallized semiconductor film as an active region; forming a second amorphous semiconductor film; forming a second semiconductor element using the second amorphous semiconductor film as an active region; attaching a support to the first semiconductor
10 element and the second semiconductor element by using an adhesive; and causing separation between the metal film and the insulating film.

It may be a method for manufacturing a semiconductor device, characterized by comprising the steps of: forming a
15 metal film, an insulating film, and a first amorphous semiconductor film in sequence over a first substrate; crystallizing the first amorphous semiconductor film; forming a first semiconductor element by using the crystallized semiconductor film as an active region; forming a second
20 amorphous semiconductor film; forming a second semiconductor element using the second amorphous semiconductor film as an active region; attaching a support to the first and the second semiconductor elements by using an adhesive; causing separation between the metal film and the insulating film; and separating
25 the support by removing the adhesive after attaching a second substrate to the separated insulating film by using an adhesive bond.

The method for manufacturing a semiconductor device is characterized in that metal oxide is formed between the metal
30 film and the insulating film.

The method for manufacturing a semiconductor device is characterized in that the separation between the metal film and the insulating film occurs between the metal film and the metal oxide film, within the metal oxide film, or between the metal
5 oxide film and the insulating film.

The method for manufacturing a semiconductor device is characterized in that the first amorphous semiconductor film and the second amorphous semiconductor film include hydrogen.

The method for manufacturing a semiconductor device is
10 characterized in that the first semiconductor element is a thin film transistor.

The method for manufacturing a semiconductor device is characterized in that the second semiconductor element is a diode or a thin film transistor.

15 The method for manufacturing a semiconductor device is characterized in that the crystallization is performed by heat treatment at such a temperature that hydrogen in the first amorphous semiconductor film is released or diffused.

The method for manufacturing a semiconductor device is
20 characterized in that the metal film is a single layer made of an element selected from the group consisting of W, Ti, Ta, Mo, Cr, Nd, Fe, Ni, Co, Zr, Zn, Ru, Rh, Pd, Os, and Ir or an alloy material or a compound material having the element as its main component, or a laminate of the metal or a mixture.

25 The method for manufacturing a semiconductor device is characterized in that the insulating film is a silicon oxide film, a silicon oxynitride film, or a metal oxide film.

The method for manufacturing a semiconductor device is characterized in that the second substrate is a plastic
30 substrate or an organic resin member.

The method for manufacturing a semiconductor device is characterized in that the semiconductor device includes an optical sensor, a photoelectric conversion element, or a solar battery.

5 In addition, another invention is a semiconductor device characterized by comprising a first semiconductor element using a crystalline semiconductor film as an active region and a second semiconductor element using an amorphous semiconductor film as an active region over an adhesive.

10 It may be a semiconductor device characterized by comprising a first semiconductor element using a crystalline semiconductor film as an active region and a second semiconductor element using an amorphous semiconductor film as an active region over a plastic substrate.

15 It may be a semiconductor device characterized by comprising a first semiconductor element using a crystalline semiconductor film as an active region and a second semiconductor element using an amorphous semiconductor film as an active region over an adhesive, wherein the first
20 semiconductor element and the second semiconductor element are electrically connected to each other.

 It may be a semiconductor device characterized by comprising a first semiconductor element using a crystalline semiconductor film as an active region and a second
25 semiconductor element using an amorphous semiconductor film as an active region over a plastic substrate, wherein the first semiconductor element and the second semiconductor element are electrically connected to each other.

 The semiconductor device is characterized in that the
30 adhesive is provided with exfoliate paper.

The semiconductor device is characterized in that the first semiconductor element is a thin film transistor

The semiconductor device is characterized in that the second semiconductor element is a diode or a thin film transistor.

The semiconductor device is characterized in that the semiconductor device includes an optical sensor, a photoelectric conversion element, or a solar battery.

10 (EFFECT OF THE INVENTION)

According to the present invention, a semiconductor device including a semiconductor element having a polysilicon film as an active region and a semiconductor element having an amorphous silicon film as an active region can be formed over a plastic substrate. Namely, an optical sensor, a photoelectric conversion element, a solar battery element, or the like including a TFT having an active region made of a polysilicon film and a diode having an active region made of an amorphous silicon film can be manufactured.

20 A semiconductor device manufactured according to the present invention can be made more lightweight and thinner compared with a conventional one, since it is formed over a plastic substrate.

In the case where a semiconductor device is an optical sensor or a photoelectric conversion device, a signal detected by a photoelectric conversion element can be amplified by an amplifying element formed of a TFT having a polysilicon film as an active region. Therefore, weak visible light can be detected even when light receiving area of the sensor is small.

30 Further, it can be made thinner since a plastic substrate

is used. Then, selectivity of an installation site is improved; accordingly, area of a mounting substrate can be reduced. In addition, light receiving area of an optical sensor, a photoelectric conversion element, or a solar battery element
5 can be enlarged.

BRIEF DESCRIPTION OF DRAWINGS

FIG.1 is a diagram showing Embodiment Mode 1 of the present invention.

10 FIG.2 is a diagram showing Embodiment Mode 2 of the present invention.

FIG.3 is a diagram showing Embodiment 1 of the present invention.

15 FIG.4 is a diagram showing Embodiment 1 of the present invention.

FIG.5 is a diagram showing Embodiment 3 of the present invention.

FIG.6 is a diagram showing Embodiment 3 of the present invention.

20 FIG.7 is a diagram showing Embodiment 3 of the present invention.

FIG.8 is a diagram showing Embodiment 1 of the present invention.

25 FIG.9 is a diagram showing Embodiment 2 of the present invention.

FIG.10 is a diagram showing Embodiment 2 of the present invention.

FIG.11 is a diagram showing a method for mounting a semiconductor device of the present invention.

30

BEST MODE FOR CARRYING OUT THE INVENTION

Hereinafter, embodiment modes of the present invention are described with reference to the drawings. However, the present invention can be carried out in other various modes.

5 As is easily known to a person skilled in the art, the mode and the detail of the invention can be variously changed without departing from the purpose and the range of the present invention. Thus, the present invention is not interpreted while limiting to the following description of this embodiment
10 mode.

(Embodiment Mode 1)

A method for manufacturing a semiconductor device including a semiconductor element having an amorphous silicon film as an active region and a semiconductor element having a
15 polysilicon film as an active region over a plastic substrate is described in this embodiment mode with reference to FIG. 1.

First, a metal film 102 is formed over a substrate 101. A single layer made of one element of W, Ti, Ta, Mo, Cr, Nd, Fe, Ni, Co, Zr, Zn, Ru, Rh, Pd, Os, and Ir or an alloy material
20 or a compound material containing the element as its main component, a laminate thereof, a single layer of nitride thereof, or a laminate thereof may be used as the metal film 102. A film thickness of the metal film 102 is set from 10 nm to 200 nm, preferably, from 50 nm to 75 nm.

25 Next, an insulating film 103 is formed over the metal film 102. At this time, a metal oxide film 100 in an amorphous state is formed between the metal film 102 and the insulating film 103 to have a thickness of approximately from 2 nm to 5 nm. In the following step of separation, separation occurs within the
30 metal oxide film 100, at the interface between the metal oxide

film 100 and the insulating film 103, or at the interface between the metal oxide film 100 and the metal film 102. A film made of a silicon oxide, silicon oxynitride, or metal oxide material may be formed as the insulating film 103 by a sputtering method
5 or a plasma CVD method. A film thickness of the insulating film 103 is preferably equal to or more than twice of the metal film 102, preferably, from 150 nm to 200 nm.

Subsequently, a film of a material containing at least hydrogen is formed over the insulating film 103. A
10 semiconductor film, a nitride film, or the like can be used as the film of a material containing at least hydrogen. The semiconductor film is formed in this embodiment mode. Thereafter, heat treatment is performed to diffuse hydrogen contained in the film of a material containing hydrogen. The
15 heat treatment may be performed at a temperature of equal to or more than 410 °C. It may be performed separately from a formation process of a crystalline semiconductor film or may be omitted by combination thereof. For example, in the case of using an amorphous silicon film containing hydrogen as the
20 film of a material containing hydrogen and heating it to form a polysilicon film, heat treatment at equal to or more than 500 °C for crystallization enables to diffuse hydrogen at the same time as forming the polysilicon film.

Then, the polysilicon film is etched to have a desired
25 shape by a known method in order to form a TFT. A TFT 104 in FIG. 1(A) includes a polysilicon film 105 having a source region, a drain region, and a channel formation region, a gate insulating film covering the polysilicon film, a gate electrode
106 formed over a channel formation region of the polysilicon
30 film, and a source electrode 107 and a drain electrode 108

connected to the source region and the drain region through an interlayer insulating film 119. Note that the interlayer insulating film 119 is formed by using a plurality of insulating films for insulating the gate electrode from the source
5 electrode and the drain electrode.

Next, a photoelectric conversion element connected to the source electrode 107 of the TFT is formed over the interlayer insulating film 119. A diode is formed as the photoelectric conversion element in this embodiment mode. First, a first
10 electrode 110 connected to the source electrode 107 is formed, and an amorphous silicon film 111 that is a photoelectric conversion layer and a second electrode 112 are formed thereover. Thereafter, the amorphous silicon film 111 and the second electrode 112 are etched to have a desired shape, thereby
15 forming the diode. Then, a wiring 114 connected to the drain electrode 108 and connected to an output terminal as well as a wiring 113 connected to the second electrode of the diode is formed.

Subsequently, a second substrate 115 to be a support for
20 fixing the semiconductor film is attached with an adhesive 116. Note that a substrate having higher rigidity than that of the first substrate 101 is preferably used as the second substrate 115. Typically, a glass substrate, a quartz substrate, a metal substrate, a ceramics substrate, or a plastic substrate can be
25 appropriately used as the second substrate 115. An adhesive made of an organic material is used as the adhesive 116. At this time, a planarizing layer may be formed in a part of the adhesive. In this embodiment mode, a water-soluble resin 116a is applied to the adhesive made of an organic material as the
30 planarizing layer. The second substrate 115 may be attached

to the TFT 104 and the diode (reference numerals 110 to 112) by attaching a member 116b with both sides thereof covered with a reactive separating adhesive (hereinafter, referred to as a double-sided sheet) thereto. The following separation step
5 can be performed with comparatively small force by using the attaching method. Various kinds of separating adhesives such as a reactive separating adhesive, a thermally separating adhesive, a photo separating adhesive such as a UV separating adhesive, and an anaerobic separating adhesive can be given as
10 the adhesive made of an organic material.

In FIG. 1(B), the first substrate 101 and the metal film 102 formed thereover are referred to as a separation body 150. In addition, a layer from the insulating film 103 to the wiring 113 connected to the second electrode of the diode and the wiring
15 114 connected to an external terminal is referred to as a laminate body 151.

Then, the metal film 102 over the first substrate 101 and the insulating film 103 are separated from each other by a physical means. Physical force is comparatively small force
20 such as a human hand, a load by using a member having a sharp edge portion such as a wedge, air pressure of a gas sprayed from a nozzle, or ultrasonic waves. Separation occurs within the metal oxide film 100, at the interface between the insulating film 103 and the metal oxide film 100, or at the interface between
25 the metal oxide film 100 and the metal film 102; thus, the separation body 150 and the laminate body 151 can be separated from each other with comparatively small force. In this way, the laminate body 151 can be separated from the separation body 150.

30 Subsequently, a third substrate 117 and the insulating

film 103 (that is, the laminate body 151) are attached to each other with an adhesive bond 118. A plastic substrate or a member made of an organic resin is used as the third substrate 117. A plastic substrate made of PET (polyethylene terephthalate),
5 PEN (polyethylene naphthalate), PES (polyether sulfide), polypropylene, polypropylen sulfide, polycarbonate, polyetherimide, polyphenylene sulfide, polyphenylene oxide, polysulfone, or polyphthalamide can be used as the plastic substrate.

10 It is important that the adhesive bond 118 is a material having higher adhesiveness between the laminate body 151 including the insulating film 103 and the third substrate 117 than that of the adhesive 116 made of an organic material between the second substrate 115 and a layer to be separated 151.

15 Various kinds of curing adhesive bonds such as a reactive curing adhesive bond, a thermosetting adhesive bond, photo-curing adhesive bond such as a UV-curing adhesive bond, and an anaerobic curing adhesive bond can be given as the adhesive bond 118.

20 Note that the insulating film 103 may be provided with an adhesive instead of the above step. In this case, exfoliate paper (separate paper, that is, a base material such as a separator and a sheet having a separation surface on either of or both sides) may be provided so that the adhesive does not
25 attach to another member. When the separate paper is separated, the adhesive can attach to an arbitrary member. Therefore, a substrate is not necessary, and a semiconductor device can be made thinner.

Subsequently, the adhesive 116 and the second substrate
30 115 are separated from the laminate body 151 as shown in FIG.

1(D). The adhesive 116 made of an organic material is reacted to heat, light, humidity, or is chemically reacted (decreasing adhesion by using water, oxygen, or the like, for example), so that the adhesive 116 made of an organic material and the second
5 substrate 115 are separated from the laminate body 151.

According to the above steps, a semiconductor device having a TFT made of a polysilicon film and an element made of an amorphous silicon film, in this embodiment mode, a diode can be formed over the plastic substrate 117 as shown in FIG. 1(E).

10 Subsequently, a method for mounting the present invention on a printed wiring board is described with reference to FIG. 11. Note that the same part as that in FIG. 1 is described by using the same reference numeral.

FIG. 11(A) is a top view of a semiconductor device formed
15 according to this embodiment mode, which is divided by laser cutting or dicing using laser light. Wirings 113, 114, and 1101 and connection wirings 1102 to 1104 for electrically connecting the wirings to wirings formed over a printed wiring board are formed on a surface of a semiconductor device 1100 manufactured
20 according to this embodiment mode.

FIG. 11(B) is a cross-sectional view of the semiconductor device mounted on a printed wiring board 1110, along (i)-(i)' in FIG. 11(A). A TFT having an active region made of a polysilicon film and a diode having an active region made of an amorphous silicon film are formed over the plastic substrate 117. Connection wirings 1102, 1103, and 1104 (not shown) each connected to wirings 113, 114, and 1101 (not shown) are provided from a surface edge portion of the semiconductor device to a backside along a side face. The wiring 113 is a wiring connected
25 to an electrode of the diode; the wiring 114 is a wiring connected
30

to a drain electrode of the TFT; and the wiring 1101 is a wiring connected to a gate electrode of the TFT. Note that the connection wirings 1102 to 1104 are conductive films containing an element such as gold, copper, nickel, platinum, or silver, and can be formed by using a known technique such as an evaporation method or plating.

The connection wirings 1102 to 1104 are mounted by connecting with wirings (reference numerals 1107 and 1108) provided over the printed wiring board through external terminals 1105 and 1106. Note that a bump made of metal (such as gold, silver, or solder), a bump made of a conductive resin, or the like can be used for the external terminals 1105 and 1106.

FIG. 11(C) and FIG. 11(D) show a mounting method different from that shown in FIG. 11(A) and FIG. 11(B). Note that the same part as that in FIG. 1, FIG. 11(A), and FIG. 11(B) is described by using the same reference numeral.

FIG. 11(C) is a top view of the semiconductor device formed according to this embodiment mode that is divided by dicing. Wirings 113, 114, and 1101 are formed as in FIG. 1(A) and connection wirings 1112 to 1114 for electrically connecting the wirings to wirings formed over a printed wiring board are formed on a surface of a semiconductor device 1100 manufactured according to this embodiment mode.

FIG. 11(D) is a cross-sectional view of the semiconductor device mounted on a printed wiring board 1110, along (ro)-(ro)' in FIG. 11(C). A TFT having an active region made of a polysilicon film and a diode having an active region made of an amorphous silicon film are formed over the plastic substrate 117. Connection wirings 1112 to 1114 each connected to wirings 113, 114, and 1101 are formed. In addition, etching holes 1117

and 1118 which penetrate the semiconductor device are formed by a known method such as trench etching, and the wirings 113, 114, and 1101 and the external terminals 1115 and 1116 are electrically connected to one another by conductive materials 1112 to 1114 through the holes. Further, the external terminals 1115 and 1116 are mounted by connecting with wirings (reference numerals 1107 and 1108) provided over the printed wiring board. Note that the conductive materials 1112 to 1114 and the external terminals 1115 and 1116 can be made of similar materials to those of the conductive materials 1102 to 1104 and the external terminals 1105 and 1106 in FIG. 11(B) respectively.

The semiconductor device manufactured in this embodiment mode can function as an optical sensor or a photoelectric conversion element. Light entering the diode is absorbed by a photoelectric conversion layer to form an optical charge. The optical charge is amplified by a TFT and is detected.

A Schottky type diode in which a photoelectric conversion layer is interposed between an anode electrode and a cathode electrode is employed as a structure of the diode in the embodiment mode. Here, a PIN type or PN type diode, an avalanche diode, or the like can also be used as the photoelectric conversion element for converting light into an electrical signal, without limiting to the diode having the above structure.

Note that a PIN photodiode is structured by a p-type semiconductor layer, an n-type semiconductor layer, and an i-type (intrinsic) semiconductor layer interposed between the p-type semiconductor layer and the n-type semiconductor layer.

In addition, a photoelectric conversion element having a photoelectric conversion layer made of an organic material,

or the like, specifically, a transparent ITO electrode, an organic pigment (perylene pigment: Me-PTC) which is vacuum evaporated thereover, and a gold electrode formed thereover, and the like may also be used as the photoelectric conversion
5 element.

Further, a TFT having amorphous silicon as an active region can be used as the photoelectric conversion element.

A lightweight and thin substrate can be used for the semiconductor device manufactured according to this embodiment
10 mode; therefore, volume thereof can be reduced compared with that of a conventional semiconductor device. Consequently, downsizing and lightweighting of electronic devices using the semiconductor devices can be achieved.

Note that a plastic substrate, typically, a lexible
15 plastic substrate is used as the third substrate 117 in this embodiment mode; besides, it is possible to attach it to an organic resin of a package in which an IC chip, or the like is sealed, or the like. In this case, area occupied by a part on a printed wiring board can be reduced. Namely, area of the
20 printed wiring board can be reduced.

(Embodiment Mode 2)

A method for manufacturing a semiconductor device over a plastic substrate, typically, a flexible plastic substrate in a different way from that in Embodiment Mode 1 is described
25 in this embodiment mode with reference to FIG. 2.

As in Embodiment Mode 1, a metal film 202, an insulating film 203, and a TFT 204 are sequentially formed over a first substrate 201 as shown in FIG. 2(A). At this time, a metal oxide film 200 in an amorphous state is formed between the metal film
30 202 and the insulating film 203 to have a thickness of

approximately from 2 nm to 5 nm, as in Embodiment Mode 1.

Note that the TFT 204 includes a polysilicon film having a source region, a drain region, and a channel formation region, a gate insulating film covering the polysilicon film, a gate electrode formed over the channel formation region of the polysilicon film, and a source electrode and a drain electrode which are connected to the source region and the drain region through an interlayer insulating film. In addition, the interlayer insulating film 217 is formed by using a plurality of insulating films for insulating the gate electrode from the source electrode and the drain electrode.

Next, a second substrate 207 is attached to the TFT 204 and the interlayer insulating film 217 thereof by using an adhesive 208 made of an organic resin. A similar adhesive to the adhesive 116 in Embodiment Mode 1 can be used for the adhesive 208 made of an organic resin. In this embodiment mode, a water-soluble resin 208a is applied as the adhesive made of an organic material; a member 208b with both sides thereof covered with a reactive separating adhesive (hereinafter, referred to as a double-sided sheet) is attached thereto; then, the second substrate 207 is attached thereto. A similar substrate to the second substrate 115 in Embodiment Mode 1 can be appropriately used as the second substrate 207.

In FIG. 2(B), the first substrate 201 and the metal film 202 are a separation body 250, and the insulating film 203 and the TFT 204 are a laminate body 251. As in Embodiment Mode 1, the metal film 202 and the insulating film 203, that is, the separation body 250 and the laminate body 251 are separated from each other by a physical means. Separation occurs within the metal oxide film 200, at the interface between the insulating

film 203 and the metal oxide film 200, or at the interface between the metal oxide film 200 and the metal film 202; thus, the separation body 250 and the laminate body 251 can be separated with comparatively small force.

5 Subsequently, a third substrate 210 and the insulating film 203 (that is, the laminate body 251) are attached to each other by an adhesive bond 209 as shown in FIG. 2(C). A similar substrate to that used as the third substrate 117 and a similar adhesive bond to that used as the adhesive bond 118 in Embodiment
10 Mode 1 can be used as the third substrate 210 and the adhesive bond 209.

 Note that the insulating film 103 may be provided with an adhesive instead of the above step, as in Embodiment Mode 1. In this case, exfoliate paper (separate paper, that is, a
15 base material such as a separator and a sheet having a separation surface on either of or both sides) may be provided so that the adhesive does not attach to another member. When the separate paper is separated, the adhesive can attach to an arbitrary member. Therefore, a substrate is not necessary, and a
20 semiconductor device can be made thinner.

 After the second substrate 207 is separated from the double-sided sheet 208b, the double-sided sheet 208b is separated as shown in FIG. 2(D). Note that the double-sided sheet 208b and the second substrate 207 may be simultaneously
25 separated from the water-soluble resin 208a.

 Subsequently, the water-soluble resin 208a is dissolved in water and is removed. When the water-soluble resin is left, it may cause a defect. Therefore, it is preferable to make the surfaces of the source electrode 213 and the drain electrode
30 214 clean by washing treatment or O₂ plasma treatment.

Next, a photoelectric conversion element 211 is formed over the source electrode 213, and a wiring 212 connected to an output terminal is formed over the drain electrode 214 as shown in FIG. 2(E). In this embodiment mode, a photoelectric
5 conversion element 211 formed of a diode is formed as in Embodiment Mode 1. A known method may be employed as a method for manufacturing the diode.

Note that the diode is used for the photoelectric conversion element 211 in this embodiment mode; however, the
10 photoelectric conversion element is not limited thereto. A TFT having amorphous silicon in an active region may be used. In addition, the one having a photoelectric conversion layer made of an organic material, and the like, specifically, a transparent ITO electrode, an organic pigment (perylene
15 pigment: Me-PTC) which is vacuum evaporated thereover, a gold electrode formed thereover, and the like may also be used as the photoelectric conversion element 211.

According to the above steps, a semiconductor device including a TFT having a polysilicon film as an active region
20 and an element having an amorphous silicon film as an active region, in this embodiment mode, a photoelectric conversion element can be formed over a plastic substrate.

Note that the semiconductor device formed in this embodiment mode can be mounted on a printed wiring board also
25 in this embodiment mode by applying the mounting method as described in Embodiment Mode 1.

(Embodiment)

[Embodiment 1]

An example of manufacturing an optical sensor including
30 a TFT having a polysilicon film as an active region and a diode

having an amorphous silicon film as an active region by using the steps of Embodiment Mode 2 is described in this embodiment with reference to FIG. 3. Note that the optical sensor of this embodiment is a non-storage type optical sensor.

5 A TFT 304 is formed over a glass substrate (first substrate 300) as shown in FIG. 3(A). A metal film 301, here, a tungsten film (film thickness: 80 nm) is formed over the glass substrate by a sputtering method, and further, an insulating film 302, here, a silicon oxide film (film thickness: 160 nm) is laminated
10 without being exposed to atmospheric air by a sputtering method. At this time, a tungsten oxide film 308 in an amorphous state is formed between the tungsten film 301 and the silicon oxide film 301 to have a thickness of approximately from 2 nm to 5 nm. Since the tungsten film and the silicon oxide film are
15 formed also on an end face of the substrate by a sputtering method, it is preferable to selectively remove them formed on the end face of the substrate by O₂ ashing or the like. In the following step of separation, separation occurs at the interface between the tungsten film 301 and the tungsten oxide film 308, within
20 the tungsten oxide film 308, or at the interface between the tungsten oxide film 308 and the silicon oxide film 302.

Subsequently, a silicon oxynitride film 303 (film thickness: 100 nm) to be a base insulating film is formed by a PCVD method, and further, an amorphous silicon film (film
25 thickness: 54 nm) is laminated without being exposed to atmospheric air.

After forming a polysilicon film by using a known technique (a solid-phase growth method, a laser crystallization method, a crystallization method using catalytic metal),
30 patterning is performed to form a polysilicon region having a

desired shape, and thus, the TFT 304 having the polysilicon region as an active region is manufactured. Formation of a gate insulating film, formation of a gate electrode, formation of a source region or a drain region by doping into an active region, 5 formation of an interlayer insulating film, formation of a source electrode or a drain electrode, activation treatment, and the like are appropriately performed. In this embodiment, a P-type channel type TFT is formed as the TFT.

In FIG. 3(A), the first substrate 300 and the tungsten 10 film 301 formed thereover are referred to as a separation body 350. In addition, a layer from the silicon oxide film 302 to the TFT 304 is referred to as a laminate body 351.

Next, an adhesive 305 which is soluble in water or alcohols is applied to an entire surface and is baked. The adhesive may 15 have any composition, for example, epoxy series, acrylate series, silicon series, or the like. Here, a film (film thickness: 30 μm) 305 made of a water-soluble resin (manufactured by TOAGOSEI Co., Ltd.: VL-WSHL10) is applied by spin-coating, and is temporarily cured, then, fully cured. 20 Note that the water-soluble resin may be cured at a time without dividing a step of curing the water-soluble resin into two stages of temporary curing and full curing.

Subsequently, treatment for partly weakening adhesiveness between the tungsten film 301 and the silicon oxide 25 film 302 is performed to make later separation easier. The treatment for partly weakening adhesiveness is carried out by partly irradiating the tungsten film 301 or the silicon oxide film 302 with laser light along the periphery of a region to be separated, or damaging the inside or a part of the interface 30 of the tungsten oxide film 301 with pressure locally applied

thereto from outside along the periphery of a region to be separated. Specifically, a hard needle such as a diamond pen may be perpendicularly pressed and moved with loading applied. Preferably, a scribe device is used, and may be moved with
5 loading applied and with press force ranging from 0.1 mm to 2 mm. Thus, it is important to make a portion that easily causes a separation phenomenon, that is, a trigger before carrying out separation. Such pretreatment as selectively (partly) weakening the adhesiveness prevents a separation defect and
10 improves a yield. Note that this step may be performed before the adhesive 305 that is soluble in water or alcohols is applied to an entire surface.

Next, a second substrate 307 is attached to the adhesive 305 made of a water-soluble resin by using a double-sided sheet
15 306. In addition, a third substrate (not shown) is attached to the first substrate 300 by using the double-sided sheet. The third substrate prevents the first substrate 300 from being damaged in the following separation step. A substrate having higher rigidity than that of the first substrate 300, for
20 example, a quartz substrate or the like is preferably used as the second substrate 307 and the third substrate. Note that the double-sided sheet is a member having a UV separating adhesive on both sides thereof in this embodiment.

Subsequently, the first substrate 300 provided with the tungsten film 301 is separated from a side of the region in which
25 adhesiveness is partly weakened by a physical means. In this embodiment, separation occurs within the tungsten oxide film 308. The first substrate 300 can be separated by comparatively small force (for example, a human hand, air pressure of a gas
30 sprayed from a nozzle, ultrasonic waves, or the like). Thus,

a layer to be separated 351 including the silicon oxide film 302 can be separated from the first substrate 300.

Since tungsten oxide remains on the surface of the silicon oxide film 302, it is removed by dry etching or the like in this embodiment. Note that the tungsten oxide film may not be necessarily removed.

Subsequently, a fourth substrate 312 and a separated layer 351 including the silicon oxide film 302 are attached to each other by an adhesive bond 311. FIG. 3(B) shows a state after separation. It is important that the adhesive bond 311 has higher adhesiveness between the oxide film 302 (and the separated layer 315) and the fourth substrate 312 than that of the double-sided sheet 306 between the second substrate 307 and the separated layer.

A polyethylene terephthalate substrate (PET substrate) is used as the fourth substrate 312. In addition, a UV curing adhesive bond is used as the adhesive bond 311.

After the second substrate 307 is separated from the double-sided sheet 306, the double-sided sheet 306 is separated from the adhesive 305 that is soluble in water or alcohols.

Thereafter, the adhesive 305 that is soluble in water or alcohols is dissolved in water and is removed. FIG. 3(C) shows a state at this time. When the adhesive that is soluble in water or alcohols is left, it may cause a defect. Therefore, it is preferable to make the surfaces of a source electrode 313 and a drain electrode 314 of the TFT clean by washing treatment or O₂ plasma treatment.

After wirings 341 and 342 each connected to the source electrode 313 and the drain electrode 314 of the TFT are formed, a wiring 343 connected to a gate electrode 315 of the TFT through

an interlayer insulating film is formed as shown in FIG. 3(D). The wiring 343 connected to the gate electrode preferably covers the polysilicon region that is an active region of the TFT and preferably has function of a light shielding film. Note that
5 the wiring 341 connected to the source electrode 313 is connected to a power line (reference numeral 406 in FIG. 4) and the wiring 342 connected to the drain electrode is connected to a second resistor (reference numeral 404 in FIG. 4) and an output terminal (reference numeral 408 in FIG. 4). Thereafter,
10 an anode electrode 344 of the diode is formed. The anode electrode 344 is connected to the wiring 343 and a first resistor (reference numeral 403 in FIG. 4) which are connected to the gate electrode of the TFT, and is formed by using a thin film containing Ni in this embodiment.

15 Then, a silicon film 345 having each conductive layer of P, I, and N is formed over the anode electrode 344 by a plasma CVD method. Here, a microcrystal layer is used for the P and N conductive layers to increase conductivity, and an amorphous layer is used for the I type conductive layer, and a film
20 thickness of the laminated silicon thin film is set 800 nm. Note that the P layer, the I layer, and the N layer are in this order from a layer in contact with the anode electrode, and a cathode electrode 346 is formed over the N layer. ITO is used for the cathode electrode 346 in this embodiment.

25 Subsequently, a wiring 347 connected to the cathode electrode 346 through the interlayer insulating film and connected to the power line (reference numeral 406 in FIG. 4) is formed. Note that, although not shown, a wiring in which the wiring 341 connected to the source electrode of the TFT is
30 connected to the power line (reference numeral 406 in FIG. 4

and a wiring in which the wiring 342 connected to the drain electrode is connected to the second resistor (reference numeral 404 in FIG. 4) and the output terminal (reference numeral 408 in FIG. 4) are exposed on the surface of the interlayer insulating film.

Thereafter, a printed wiring board and the output terminal of the optical sensor are connected by using an anisotropic conductive film (ACF), a flexible printed circuit (FPC), a TAB (Tape Automated Bonding) tape, or a TCP (Tape Carrier Package).

FIG. 8 is a top view of a module of an electronic device to which this embodiment is applied and a cross-sectional view thereof.

FIG. 8(A) shows an appearance of a module on which a panel 800 is mounted. The panel 800 is provided with a pixel portion 803, a scanning line driver circuit 804 for selecting a pixel included in the pixel portion 803, and a signal line driver circuit 805 for supplying a video signal to the selected pixel.

In addition, a printed wiring board 806 is provided with a controller 801, a power supply circuit 802, and an optical sensor 810 provided through an FPC 809, and various kinds of signals and power supply voltage output from the controller 801 or the power supply circuit 802 are supplied through the FPC 807 to the pixel portion 803, the scanning line driver circuit 804, and the signal line driver circuit 805 of the panel 800.

The power supply voltage and the various kinds of signals are supplied to the printed wiring board 806 through an interface (I/F) portion 808 in which a plurality of input terminals is disposed.

FIG. 8(B) is a cross-sectional view along (K)-(K)' in FIG.

8(A). Since the FPC 807 is used for connection with the printed wiring board in this embodiment, the optical sensor 810 can be disposed over a package of an IC chip 811, a CPU, or the like which is disposed over the printed wiring board 806. In
5 addition to enlarging light receiving area of the optical sensor, area of the printed wiring board can be narrowed.

FIG. 4 is a circuit diagram of a non-storage type optical sensor formed according to this embodiment. The diode (the anode electrode 344, the silicon semiconductor film 345, and
10 the cathode electrode 346) in FIG. 3 corresponds to reference numeral 401 in FIG. 4. Note that the cathode electrode 346 of the diode is connected to the power line 406, and the anode electrode 344 is connected to the first resistor 403 and a gate electrode 407 of the TFT 402. In addition, the source electrode
15 of the TFT is connected to the power line 406, and the drain electrode is connected to the output terminal 408 and the second resistor 404. Electromotive force generated in the diode 401 is applied to the gate electrode 407 of the TFT 402. Then, current flowing through the TFT 402 and the second resistor 404
20 is converted into voltage from a resistance value, and is detected by a voltage difference between the output terminal 408 and ground potential.

In this embodiment, the anode electrode 344 of the diode connected to the TFT 402 is made of Ni, and the cathode electrode
25 346 is made of ITO; however, the present invention is not limited to this structure. The anode electrode 344 may be a light transmitting conductive film, and the cathode electrode 346 may be a metal electrode. In this case, it is preferable to form a light shielding film in a lower part of the silicon film since
30 the TFT is affected when light enters the TFT.

The anisotropic conductive film is used in this embodiment to connect the optical sensor to the printed wiring board; however, the present invention is not limited thereto. It is possible to connect by using conductive paste such as
5 solder.

The optical sensor formed according to this embodiment includes an amplifying element formed of a diode having an active region made of an amorphous silicon film and a TFT having an active region made of a polysilicon film. Therefore, it can
10 detect weak light even when a photoelectric conversion layer (light receiving layer) is small in area, that is, small size. In addition, the optical sensor can be made more lightweight and thinner compared with a conventional one, since it is formed over a plastic substrate. When the anisotropic conductive film
15 is used for connection with the printed wiring board, the optical sensor can be disposed over a package of an IC chip, a CPU, or the like which is disposed over the printed wiring board. In addition to enlarging light receiving area of the optical sensor, area of the printed wiring board can be
20 narrowed.

Note that Embodiment Mode 2 is applied to this embodiment, but this embodiment can be combined with Embodiment Mode 1.
[Embodiment 2]

An example of manufacturing an optical sensor including
25 a TFT having a polysilicon film as an active region and a diode having an amorphous silicon film as an active region by using the steps of Embodiment Mode 2 is described in this embodiment with reference to FIG. 9. Note that an optical sensor of this embodiment is a storage type optical sensor, and an image of
30 a facsimile machine, a scanner, and a radiation such as an X-ray

can be read by using a plurality of one bit that is one pixel of the optical sensor, and high-performance and large-area photoelectric conversion device can be manufactured.

As shown in FIG. 9(A), a metal film 901 and an insulating
5 film 902 are formed over a glass substrate (first substrate 900) as in Embodiment 1. In this embodiment, a tungsten film (film thickness: from 10 nm to 200 nm, preferably from 50 nm to 75 nm) is formed as the metal film 901, and further, the insulating film 902, here, a silicon oxide film (film thickness: from 150
10 nm to 200 nm) is laminated without being exposed to atmospheric air.

Subsequently, a silicon oxynitride film 903 (film thickness: 100 nm) to be a base insulating film is formed by a PCVD method, and an amorphous silicon film (film thickness:
15 54 nm) is laminated without being exposed to atmospheric air. At this time, a tungsten oxide film 915 in an amorphous state is formed between the tungsten film 901 and the silicon oxide film 902 to have a thickness of approximately from 2 nm to 5 nm.

20 The amorphous silicon film contains hydrogen, and in the case of forming a polysilicon film by heating, heat treatment at equal to or more than 500 °C for crystallization enables to diffuse hydrogen at the same time as forming the polysilicon film. A TFT can be formed by using the obtained polysilicon
25 film. At this time, the tungsten oxide film 915 in an amorphous state is also crystallized.

Here, the polysilicon film is formed by using a known technique (a solid-phase growth method, a laser crystallization method, a crystallization method using catalytic metal, or the
30 like). Subsequently, the polysilicon film is patterned to form

a silicon region having a desired shape, and thus, a TFT 904 having the polysilicon region as an active region is manufactured. Formation of a gate insulating film, formation of a gate electrode, formation of a source region or a drain region by doping into the active region, formation of an interlayer insulating film, formation of a source electrode or a drain electrode, activation treatment, and the like are appropriately performed. In this embodiment, a P channel type TFT is formed as the TFT.

10 Subsequently, a wiring 907 connected to a source electrode 905 of the TFT 904 is formed. Note that the wiring 907 connected to the source electrode 905 is an anode electrode of a diode.

15 Then, a silicon semiconductor film 909 having each conductive layer of P, I, and N is formed over the anode electrode 907 by a plasma CVD method. Here, the silicon semiconductor film having each conductive layer of P, I, and N can be manufactured according to similar steps to those in Embodiment 1. Thereafter, a cathode electrode 914 is formed over the silicon semiconductor film. In this embodiment, ITO is used for the cathode electrode.

20 Subsequently, a wiring 910 connected to the cathode electrode and a wiring 908 connected to a drain electrode 906 of the TFT through an interlayer insulating film are formed. 25 The wiring 910 is connected to a power line (reference numeral 1002 in FIG. 10(A)), and the wiring 908 is connected to a signal wiring (reference numeral 1004 in FIG. 10(A)).

30 In FIG. 9(A), the glass substrate 900 and the metal film 901 formed thereover are referred to as a separation body 950. In addition, a layer from the oxide film 902 to the wiring 910

connected to the diode and the cathode electrode of the diode is referred to as a laminate body 951.

Subsequently, an adhesive 911 that is soluble in water or alcohols is applied to an entire surface of the laminate body, and is baked. The adhesive 911 that is soluble in water or alcohols may have any composition, for example, epoxy series, acrylate series, silicon series, or the like. Here, a film (film thickness: 30 μm) made of a water-soluble resin (manufactured by TOAGOSEI Co., Ltd.: VL-WSHL10) is applied by spin coating, and is temporarily cured, then, fully cured. Note that the water-soluble resin may be cured at a time without dividing a step of curing the water-soluble resin into two stages of temporary curing and full curing. Subsequently, treatment for partly weakening adhesiveness between the metal film 901 and the oxide film 902 is performed to make later separation easier. This step may be similar one to that in Embodiment 1.

Then, a holding substrate 913 is attached to the adhesive 911 that is soluble in water or alcohols by using a double-sided sheet 912. After the adhesiveness is partly weakened as described in Embodiment 1, separation is caused from a side of the region in which the adhesiveness is partly weakened, and the glass substrate 900 provided with the metal film 901 is separated by a physical means. In this embodiment, separation occurs within the tungsten oxide film 915. When the tungsten oxide film remains on the surface of the oxide film 902, the tungsten oxide film is preferably removed by dry etching or the like. In this way, a layer to be separated 951 including the oxide film 902 can be separated from the glass substrate 900.

Next, a plastic substrate 922 and the separated layer 951

including the oxide film 902 are attached to each other by an adhesive bond 921 as shown in FIG. 9(B). It is important that the adhesive bond 921 has higher adhesiveness between the oxide film 902 (and the separated layer 951) and the plastic substrate 922 than that of the double-sided sheet 912 between the holding substrate 913 and the separated layer 951.

A polycarbonate substrate (PC substrate) is used as the plastic substrate 922. In addition, a UV curing adhesive bond is used as the adhesive bond 921.

10 After the holding substrate 913 is separated from the double-sided sheet 912, the double-sided sheet 912 is separated from the adhesive 911 that is soluble in water or alcohols.

Thereafter, the adhesive 911 that is soluble in water or alcohols is dissolved in water and is removed. When the 15 adhesive bond is left, it may cause a defect. Therefore, it is preferable to make the surfaces of the wiring 910 connected to the cathode electrode 914 of the diode and the wiring 908 connected to the drain electrode of the thin film transistor clean by washing treatment or O₂ plasma treatment.

20 Thereafter, exposed wirings 908 and 910 on the surface of the optical sensor are connected to the signal wiring (reference numeral 1004 in FIG. 10(A)) and the power line (reference numeral 1002 in FIG. 10(A)) respectively by using a module provided with an anisotropic conductive film (ACF), 25 a flexible printed circuit (FPC), a TAB (Tape Automated Bonding) tape, or a TCP (Tape Carrier Package), a TAB tape, or a TCP.

FIG. 10(A) shows an equivalent circuit of one bit that is one pixel of the storage type optical sensor formed according to this embodiment. In FIG. 10(A), the equivalent circuit 30 includes a diode 1001 in which the anode electrode 907 is

connected to the power line 1002 and the cathode electrode 914 is connected to the source electrode of a TFT 1003 and the TFT 1003 for transferring an optical charge stored in the diode by a transfer switch function according to a control signal of a gate electrode. The drain electrode of the TFT is connected to the signal wiring 1004. The charge generated in the diode is transferred to a capacitor (not shown) over the signal wiring through the TFT, and is read by a read out circuit (not shown) connected to the signal wiring.

FIG. 10(B) shows an equivalent circuit in the case of arranging the equivalent circuit of one bit shown in FIG. 10(A) in a 3 by 3 array. A driving method is described with reference to FIG. 10(B).

First, a gate signal line g1 of a shift register SR1 is activated to turn on charge transfer transistors T11 to T13 of the pixels in the first column, and optical charges of diodes SS11 to SS13 are output to signal wirings S1 to S3. Next, control signals of transfer switches M1 to M3 of a shift register SR2 are sequentially made active, and optical charges of SS11 to SS13 which are amplified by a buffer amplifier (Amp) are read by Vout in chronological order. Then, a gate signal line g2 of the shift register SR1 is activated. Such a procedure is repeated to read the optical charge of each pixel, that is, the diode.

In this embodiment, the anode electrode 907 of the diode connected to the TFT is made of Ni, and the cathode electrode 914 is made of ITO; however, the present invention is not limited to this structure. The anode electrode 907 may be a light transmitting conductive film, and the cathode electrode 914 may be a metal electrode. In this case, it is preferable to form

a light shielding film in a lower part of the silicon film since the TFT is affected when light enters the TFT.

In addition, the anisotropic conductive film is used to connect the wirings 910 and 908 exposed on the surface of the optical sensor to the power line (reference numeral 1002 in FIG. 10(A)) and the signal wiring (reference numeral 1004 in FIG. 10(A)) respectively; however, the present invention is not limited thereto. They can be connected by the mounting method as described in Embodiment Mode 1.

According to the above steps, a photoelectric conversion device including a plurality of optical sensors can be formed over a plastic substrate. Namely, a photoelectric conversion device provided with a plurality of optical sensors including a TFT having a polysilicon as an active region and a diode having amorphous silicon as an active region can be manufactured.

The photoelectric conversion device formed according to this embodiment includes a plurality of optical sensors formed of an amplifying element which has a diode made of an amorphous silicon film and a TFT made of a polysilicon film. Therefore, it can detect weak light and is highly sensitive even when a photoelectric conversion layer (light receiving layer) is small in area, that is, small size. In addition, the photoelectric conversion device can be made more lightweight and thinner compared with a conventional one, since it is formed over a plastic substrate. When an anisotropic conductive film is used for connection with a driver circuit such as a shift register or a power line, the photoelectric conversion device can be placed over a package composed of an IC chip, a driver circuit, a power supply circuit, or the like which is disposed over the printed wiring board. In addition to enlarging light receiving

area of the photoelectric conversion device, area of the printed wiring board can be reduced.

[Embodiment 3]

An example of manufacturing an electronic device having
5 an integrated circuit (IC) composed of a semiconductor element
having a polysilicon film as an active region and a
semiconductor element having an amorphous silicon as an active
region, typically, an IC card over a plastic substrate is
described here with reference to FIGS. 5 to 7. In this
10 embodiment, a card type calculator as shown in FIG. 5 is given
as an IC card for explanation. FIG. 5(A) is a top view of the
card type calculator, and FIG. 5(B) is a top view of a module
of the card type calculator formed over a plastic substrate.
Note that the one provided with a keypad 503 by a known method
15 is used as the plastic substrate in this embodiment. A
calculator which uses a solar battery 501 as a power source and
an EL display device for a display portion 502 that is a part
of an output portion and which has a driver circuit 504 of the
display portion, a keypad 503 that is a part of an input portion,
20 a central processing unit 505 (CPU) and a memory 506, and a power
supply circuit 507 connected to the solar battery, as shown in
FIG. 5(A), and a manufacturing method thereof are described.

FIG. 6 is a block diagram of the IC card, in this embodiment,
the card type calculator. Reference numeral 601 denotes a
25 central processing unit (hereinafter, referred to as a CPU);
602, a control portion; 603, an operation portion; 604, a
memory; 605, an input portion; 606, an output portion; and 607,
a power supply portion.

The CPU 601 includes the operation portion 603 and the
30 control portion 602. The operation portion 603 is composed of

an arithmetic logic unit (ALU) for performing arithmetic operations such as addition and subtraction and logical operations such as AND, OR, and NOT, various registers for temporarily storing data or results of the operations, a counter
5 for counting the number of input 1, and the like.

Circuits composing the operation portion 603, such as an AND circuit, an OR circuit, a NOT circuit, a buffer circuit, and a resistor circuit can be formed of TFTs. A semiconductor film that is crystallized by using continuous wave laser light
10 may be formed as an active region of the TFT to obtain high field effect mobility. A method for obtaining a polysilicon film by irradiating an amorphous silicon film with continuous wave laser light may be employed. A method for obtaining a polysilicon film by irradiating with continuous wave laser
15 light after obtaining a polysilicon film by heating an amorphous silicon film may also be adopted. Moreover, a method for obtaining a polysilicon film by irradiating with continuous wave laser light after adding a metal element which serves as a catalyst to an amorphous silicon film and obtaining a
20 polysilicon film by heating may be employed. In this embodiment, a channel length direction of the TFT composing the operation portion 603 and a scanning direction of a laser beam are arranged in the same direction.

The control portion 602 has a function of executing an
25 instruction stored in the memory 604 and controlling the whole operation. The control portion 602 includes a program counter, an instruction register, and a control signal generating portion. In addition, the control portion 602 can also be formed of the TFTs and can be manufactured by using a polysilicon
30 film crystallized with continuous wave laser light as an active

region of the TFT. In this embodiment, a channel length direction of the TFT composing the control portion 602 and a scanning direction of a laser beam are arranged in the same direction.

5 The memory 604 is a portion that stores data and instructions for performing calculation, and data or programs that are often executed in the CPU are stored. The memory 604 includes a main memory, an address register, and a data register. A cache memory in addition to the main memory may be used. These
10 memories may include an SRAM, a DRAM, a flash memory, or the like. When the memory 604 is also composed of TFTs, it can be manufactured by using a crystallized polysilicon film with continuous wave laser light as an active region of the TFTs. In this embodiment, a channel length direction of the TFT
15 composing the memory 604 and a scanning direction of a laser beam are arranged in the same direction.

 The input portion 605 is a device that receives data or programs from the outside. The output portion 606 is a device for displaying results, typically, a display device.

20 The power supply portion 607 is a device that supplies necessary electric power for operating the CPU or the like. In this embodiment, the power supply portion includes a solar battery. Note that a secondary battery storing electric power generated in the solar battery may be included. When an
25 electroluminescence display (EL display) is used for a display device of the output portion 606, power consumption is low, and therefore, drive power is low. A circuit and a capacitor element of the power supply portion can be formed of a TFT. In this case, the TFT can be manufactured by using a polysilicon
30 film crystallized with continuous wave laser light as an active

region. In this embodiment, a channel length direction of the TFT composing the power supply portion and a scanning direction of a laser beam are arranged in the same direction.

5 A CPU with few variations can be formed over an insulating substrate by arranging a channel length direction of the TFT and a scanning direction of a laser beam in the same direction. Although a circuit design and a manufacturing step become complicated, a CPU, an output portion, a memory, and a power supply portion can be formed over the same substrate. It is
10 preferable to arrange a channel length direction of a plurality of TFTs disposed in each pixel and a scanning direction of a laser beam in the same direction in the display portion.

An example of transferring a module of a card type calculator formed over a glass substrate onto a plastic
15 substrate provided with a keypad is described hereinafter with reference to FIG. 7. FIG. 7 is a cross-sectional view along (L)-(L)' in FIG. 5(B). As in Embodiment 1, a silicon oxide film 703 is formed over a glass substrate 701 with a tungsten film 702 therebetween. At this time, a tungsten oxide film 712 in
20 an amorphous state is formed between the tungsten film 702 and the silicon oxide film 703 to have a thickness of approximately from 2 nm to 5 nm. Next, an amorphous silicon film is formed over the silicon oxide film. Thereafter, a crystalline silicon film is formed by a known method, and this film is used for an
25 active region of a TFT of a pixel region 751, a TFT of a driver circuit 752 of a pixel, a TFT of a CPU 753, a capacitor element of a memory 755, or the like. Then, n-channel type TFTs 705, 707, and 709, p-channel type TFTs 704, 706, and 708, capacitor portions 710 and 711, a terminal portion (not shown), and the
30 like are formed by a known method. A CMOS circuit can be formed

by complementarily combining the n-channel type TFT 707 and the p-channel type TFT 706, and the n-channel type 709 and the p-channel type TFT 708 respectively, and various integrated circuit such as the CPU and the driver circuit can be formed.

5 Note that it is preferable to employ a method using continuous wave laser light as described in this embodiment for a method for forming an active region of the CPU, the driver circuit, or the like.

Subsequently, a solar battery 721 connected to a drain
10 electrode of a TFT (not shown) of a power supply circuit is formed in a power supply portion 754. Specifically, a diode having an active region made of amorphous silicon 723 is formed over a conductive film 722 connected to the TFT of the power supply circuit. Note that the capacitor element 711 connected to the
15 solar battery is formed in a lower portion of the solar battery in this embodiment. This is because it primarily stores electric energy generated in the solar battery. Electric energy is not run out during use and it can be used in a dark place.

20 Next, a pixel 724 connected to a drain electrode of the switching TFT 704 in the pixel region is formed. In this embodiment, an EL display device is used as a display device. Note that a known display device such as a liquid crystal display device can also be used.

25 Subsequently, a lead wiring, an input-output terminal, and the like are appropriately formed after forming an insulating film covering these elements.

Then, a holding substrate 732 is attached by an adhesive 731 (removable adhesive such as a water-soluble adhesive or a
30 double-sided sheet) (FIG. 7(A)).

Subsequently, the glass substrate 701 and the tungsten film 702 are separated from the silicon oxide film 703 by applying mechanical force between the metal film 702 and the oxide film 703. In this embodiment, separation occurs within
5 the tungsten oxide film 712. When the tungsten oxide remains on the surface of the silicon oxide film, the tungsten oxide may be removed by dry etching or the like. Thereafter, a plastic substrate 734 provided with a keypad is fixed to the surface of the silicon oxide film 703 with an adhesive bond 733
10 therebetween.

Subsequently, the holding substrate 732 is removed by removing the adhesive 731 (FIG. 7(B)). Thereafter, a protective film (not shown) such as a sticker in which numerical number and a mark of a keyboard are drawn on its surface is formed.
15 In this way, an integrated circuit (IC) including a TFT having crystalline silicon as an active region and a diode having amorphous silicon as an active region can be completed over the plastic substrate 734. Namely, an IC card of a card type calculator or the like including the power supply portion 754
20 formed by using a solar battery, the pixel region 751, an integrated circuit (IC) including the driver circuit 752 of a pixel, the CPU 753, the memory 755, and the like can be formed over the plastic substrate.

An electronic device manufactured according to this
25 embodiment, such as an IC card, is formed over a plastic substrate; therefore, it is thin and lightweight. In addition, a power supply portion, an input portion, a central processing unit, an output portion, and the like are formed over the same substrate; therefore, there is no step of attaching a plurality
30 of panels, and throughput can be improved.